

Applicant: GOYA IMPORTACIONES Y DISTRIBUCIONES S.L.

Address: PLATAFORMA LOGISTICA DE ZARAGOZA C/TRAPANI 27EDIFICIO 50197 SPAIN

The following merchandise was (were) submitted and identified by client as:

Sample Name: SCARF

Model No.: 37039

Manufacturer: GOYA IMPORTACIONES Y Exported to: CHINA

DISTRIBUCIONES S.L.

Supplier: GOYA IMPORTACIONES Y Country of Origin: CHINA

DISTRIBUCIONES S.L.

Sample Received Date: Dec. 26, 2016
Completed Date: Dec. 29, 2016

Test Result(s): Please refer to next page(s).

Test Requested and Conclusion(s):

| No. | Test Sample | Standard and Requirement | Conclusion(s) |
|-----|---------------------------------------|----------------------------------------------------------------------------------------------|--------------------------------------------------|
| 1 | Tested materials of submitted samples | Client's requirement (For reference OEKO-TEX Standard 100:2016) - Cleavable arylamines (AZO) | PASS (Please refer to "N" note of the next page) |
| 2 | Tested materials of submitted samples | Class II on client's requirement (For reference OEKO-TEX Standard 100:2016) - Formaldehyde | PASS (Please refer to "N" note of the next page) |

Signed for and on Behalf of CTT

Yuhu / Lab supervisor

Consumer Testing Technology Co., Ltd.

This test report is issued by the company subject to its General Conditions of Services printed overleaf or available on request and accessible at www.cttlab.com . Attention is drawn to the limitations of liability, indemnification and jurisdictional issues defined therein. Unless otherwise stated the results shown in this report refer only to the sample(s) tested. Without prior written permission of the company, this test report cannot be reproduced, except in full. Items marked with "n" or "m" means they are not accredited by CNAS or CMA, "s" means the item of subcontractor is not accredited by CNAS or CMA.



Test Result(s):

Cleavable Arylamines (AZO) - Client's requirement (For reference OEKO-TEX Standard 100) ^s

<u>Method:</u> OEKO - TEX Testing Procedures, analyzed by Gas Chromatograph-Mass Spectrometry (GC-MS)/

High Performance Liquid Chromatograph (HPLC-DAD).

| No. | Substances Name | CAS No. | Limit | Result (mg/kg) |
|------------|-------------------------------------------------------------------------------|----------|---------|------------------|
| 110. | oubstances Name | OAO NO. | (mg/kg) | 1+2 ^N |
| 1 | biphenyl-4-ylamine/ 4-aminodiphenyl/ xenylamine | 92-67-1 | 20 | N.D. |
| 2 | benzidine | 92-87-5 | 20 | N.D. |
| 3 | 4-chloro-o-toluidine | 95-69-2 | 20 | N.D. |
| 4 | 2-naphthylamine | 91-59-8 | 20 | N.D. |
| 5∆ | o-aminoazotoluene/ 4-o-tolylazo-o-toluidine/ 4-amino-2', 3-dimethylazobenzene | 97-56-3 | 20 | N.D. |
| 6∆ | 2-amino-4-nitrotoluene/ 5-nitro-o-toluidine | 99-55-8 | 20 | N.D. |
| 7 | 4-chloroaniline/p-chloroaniline | 106-47-8 | 20 | N.D. |
| 8 | 4-methoxy-m-phenylenediamine/2,4-diaminoanisole | 615-05-4 | 20 | N.D. |
| 9 | 4,4'-methylenedianiline/ 4,4'-diaminodiphenylmethane | 101-77-9 | 20 | N.D. |
| 10 | 3,3'-dichlorobenzidine/ 3,3'-dichlorobiphenyl-4,4'-ylenediamine | 91-94-1 | 20 | N.D. |
| 11 | 3,3'-dimethoxybenzidine/ o-dianisidine | 119-90-4 | 20 | N.D. |
| 12 | 3,3'-dimethylbenzidine/ 4,4'-bi-o-toluidine | 119-93-7 | 20 | N.D. |
| 13 | 4,4'-methylenedi-o-toluidine/ 3,3'-Dimethyl-4,4'-diaminobiphenylmethane | 838-88-0 | 20 | N.D. |
| 14 | 6-methoxy-m-toluidine/ p-cresidine | 120-71-8 | 20 | N.D. |
| 15 | 4,4'-methylene-bis-(2-chloroaniline)/ 2,2'-dichloro-4,4'-methylene-dianiline | 101-14-4 | 20 | N.D. |
| 16 | 4,4'-oxydianiline | 101-80-4 | 20 | N.D. |
| 17 | 4,4'-thiodianiline | 139-65-1 | 20 | N.D. |
| 18 | o-toluidine/ 2-aminotoluene | 95-53-4 | 20 | N.D. |
| 19 | 4-methyl-m-phenylenediamine/ 2,4-toluylendiamine | 95-80-7 | 20 | N.D. |
| 20 | 2,4,5-trimethylaniline | 137-17-7 | 20 | N.D. |
| 21 | o-anisidine / 2-methoxyaniline | 90-04-0 | 20 | N.D. |
| 22◊ | 4-aminoazobenzene | 60-09-3 | 20 | N.D. |
| 23 | 2,4-xylidine | 95-68-1 | 20 | N.D. |
| 24 | 2,6-xylidine | 87-62-7 | 20 | N.D. |
| Conclusion | | | | PASS |

This test report is issued by the company subject to its General Conditions of Services printed overleaf or available on request and accessible at www.cttlab.com . Attention is the unit to the limitations of liability, indemnification and jurisdictional issues defined therein. Unless otherwise stated the results shown in this report refer only to the sample(s) tested. Without prior written permission of the company, this test report cannot be reproduced, except in full. Items marked with "n" or "m" means they are not accredited by CNAS or CMA. "Single the temporal produced of the company of the company that the test report cannot be reproduced, except in full. Items marked with "n" or "m" means they are not accredited by CNAS or CMA.



Note: 1. mg/kg = milligram per kilogram (ppm).

- 2. N.D. = Not Detected (< RL).
- 3. RL (Reporting Limit) = 20 mg/kg.
- 4. "△" = The CAS No. 97-56-3 (No.5) and 99-55-8 (No.6) are further reduced to CAS No.95-53-4(No.18) and 95-80-7(No.19).
- 5. "⋄" = Azo colorants that are able to form 4-aminoazobenzene(No.22), generate under the condition of this method aniline and 1, 4-phenylenediamine, therefore, the method of § 64 LFGB, BVL, B 82.02.9 was employed to verify the 4-aminoazobenzene.
- 6. "N" = This data is obtained from composite testing on more than one materials, it is possible that result obtained from individual testing on any one of the materials is substantially higher.

 Please be cautious when using this data for compliance evaluation.

Formaldehyde - Client's requirement (For reference OEKO-TEX Standard 100)

Method: OEKO - TEX Testing Procedures, analyzed by Ultraviolet visible Spectroscopy (UV-Vis).

| Meterial No | Limit (mg/kg) | | | Describ (mention) | Complusion | |
|------------------|---------------|----|-----|-------------------|----------------|------------|
| Material No. | I | П | Ш | IV | Result (mg/kg) | Conclusion |
| 1+2 ^N | N.D. | 75 | 300 | 300 | N.D. | PASS |

Note: 1. mg/kg = milligram per kilogram (ppm).

- 2. N.D. = Not Detected (< RL).
- 3. RL (Reporting Limit) = 16 mg/kg.
- 4. Product Class:

I = products for babies.

 Π = products with direct contact to skin.

Ⅲ = products without direct contact to skin.

IV = decoration materials.

5. "N" = This data is obtained from composite testing on more than one materials, it is possible that result obtained from individual testing on any one of the materials is substantially higher. Please be cautious when using this data for compliance evaluation.

Test Material List

The following materials apply only to the samples submitted for chemical testing

| Material No. | Description | Location |
|--------------|-----------------------|----------|
| 1 | Beige synthetic fiber | Scarf |
| 2 | Black synthetic fiber | Scarf |

This test report is issued by the company subject to its General Conditions of Services printed overleaf or available on request and accessible at www.cttlab.com . Attention is than to the limitations of liability, indemnification and jurisdictional issues defined therein. Unless otherwise stated the results shown in this report refer only to the sample(s) tested. Without prior written permission of the company, this test report cannot be reproduced, except in full. Items marked with "n" or "m" means they are not accredited by CNAS or CMA.



Photo of Sample:



End of Report

This test report is issued by the company subject to its General Conditions of Services printed overleaf or available on request and accessible at www.cttlab.com . Attention is the limitations of liability, indemnification and jurisdictional issues defined therein. Unless otherwise stated the results shown in this report refer only to the sample(s) test of without prior written permission of the company, this test report cannot be reproduced, except in full. Items marked with "n" or "m" means they are not accredited by CNAS or CMA, "a means the item of subcontractor is not accredited by CNAS or CMA.